



(19)

Generated Document

(11) Publication number: 01318080 A

PATENT ABSTRACTS OF JAPAN

(21) Application number: 63148219

(51) Intl. Cl.: C09K 17/00

(22) Application date: 17.06.88

(30) Priority:	(71) Applicant: ASAHI CHEM IND CO LTD
(43) Date of application publication: 22.12.89	(72) Inventor: MOTOMURA OSAMU
(84) Designated contracting states:	(74) Representative:

**(54) GROUT AND
UNDERGROUND
FORMATION OF CURED
OBJECT BY USING THE
SAME GROUT**

(57) Abstract:

PURPOSE: To obtain a grout improved in flow so as to be pumped from the ground by mixing a cement with calcium silicate hydrate powder, a fine aggregate and mixing water.

CONSTITUTION: A calcium material, a silicic material, etc., are

<https://www.delphion.com/cgi-bin/viewpat.cmd/JP01318080A2>


7/16/2004

01318080 A

Page 2 of 3

subjected to a hydration reaction, followed by atmospheric pressure steam curing, a high-temperature high-pressure steam curing, etc., and ground to obtain a calcium silicate hydrate powder (A) of a particle diameter of 1mm or below, represented by the formula (wherein X, Y and Z are positive integers). 100 pts.wt. cement (B) (e.g., portland cement) is mixed with 150-250 pts.wt. component A, 200-500 pts.wt. fine aggregate (C), and 70-110wt%, based on the total amount of components A and B, mixing water to obtain a grout. Said grout is pumped from the ground into a water-permeable bag inserted into the ground, whereupon said bag is expanded while excessive water is removed from the grout to form an underground cured object.

COPYRIGHT: (C)1989, JPO&Japio



L4 ANSWER 210 OF 299 CA COPYRIGHT 2004 ACS on STN
AN 113:83906 CA
ED Entered STN: 01 Sep 1990
TI Grout and strengthening of soil by the grout
IN Motomura, Osamu
PA Asahi Chemical Industry Co., Ltd., Japan
SO Jpn. Kokai Tokkyo Koho, 8 pp.
CODEN: JKXXAF
DT Patent
LA Japanese
IC ICM C09K017-00
CC 58-5 (Cement, Concrete, and Related Building Materials)
FAN. CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 01318080	A2	19891222	JP 1988-148219	19880617
PRAI	JP 1988-148219		19880617		

AB The grout comprises cement 100, hydrated Ca silicate powder 150-250, and fine aggregate 200-500 wt. parts with 70-110 wt.% (based on cement and hydrated Ca silicate) mixing water. The grout is pumped into water-permeable bags inserted into soil foundation and hardened to strengthen the foundation.

ST grout cement silicate soil strengthening

IT Grout
(cement, hydrated calcium
silicate in, for soil strengthening)

IT Aggregates
(fine, grout contg., hydrated calcium
silicate and aggregate in, for soil strengthen